



# Technical data sheet

<b>Name</b>	<b>Belgian Blue</b>
<b>Petrographic Designation</b>	Limestone
<b>Colour</b>	Grey / Blue
<b>Origin</b>	Belgium

Test:

Porosity by volume	TV220 - BBRI	Mean Value	0,28	%
Apparent Density	EN 1936	Mean Value	2687	Kg / m3
Compressive Strength	TV220-BBRI	Mean Value	157,9	N/mm2
Wear Resistance	Capon TV220-BBRI	Mean Value	2,87	Mm/1000m
Flexural Strength	EN 1926	Mean Value	16,7	N/mm2