

# Technical data sheet

| Name                            | Cream Fatima |
|---------------------------------|--------------|
| <b>Petrographic Designation</b> | Limestone    |
| <b>Colour</b>                   | Light Beige  |
| <b>Origin</b>                   | Portugal     |
|                                 |              |

| Test                                      | Mean Value | Units                           |
|---|------------|---------------------------------|
| Apparent Density                          | 2435       | Kgs/m <sup>3</sup>              |
| Flexural Strength                         | <b>15</b>  | <b>MPa</b>                      |
| Slip Resistance                           | 78         | USVR - Dry                      |
|   | 15         | USVR - Wet                      |
| Frost resistance                          |            | No changes after 48 test cycles |
| Thermal Shock Resistance                  |            | NA                              |
| Open Porosity                             | 4,58       | %                               |
| Abrasion Resistance                       | 20,5       | mm - Capon                      |
| Water Absorption @ atmospheric conditions | 1,9        | %                               |
| Reactio to fire                           | Class 1    | Not tested                      |
| Surface Finish                            |            | Polished, honed, bush hammered, |
|   |            |                                 |