

Technical data sheet

Name	Moleanos Blue
Petrographic Designation	Limestone
Colour	Gray / Blueish
Origin	Portugal

Test	Mean Value	Units
Apparent Density	2420	Kg/m ³
Flexural Strength	10,7	MPa
Flexural Strength after Frost Resistance	9,0	MPa
Resistance to fixing	297	Kg
Water Absorption	3,1	%
Apparent Porosity	8,5	%
Thermal Shock Resistance	0,07	%
Abrasion Test	26	mm
Frost Resistance	48	Cycles with no alterations
Slip Resistance Dry	66	USVR
Slip Resistance Wet	75	USVR